

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 426 385 A1**

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art. 158(3) EPC

(43) Date of publication:

09.06.2004 Bulletin 2004/24

(21) Application number: 02754132.5

(22) Date of filing: 17.06.2002

(51) Int Cl.7: **C08F 4/60, C08F 10/02**

(86) International application number:
PCT/CN2002/000425

(87) International publication number:
WO 2003/010207 (06.02.2003 Gazette 2003/06)

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: 23.07.2001 CN 01126323

09.02.2002 CN 02110844

(71) Applicant: **SHANGHAI INSTITUTE OF ORGANIC
CHEMISTRY, CHINESE ACADEMY OF SCIENCES**
Shanghai 200032 (CN)

(72) Inventors:

• **SUN, Xiuli**
Shanghai 200032 (CN)

• **HU, Weiqiu**
Shanghai 200032 (CN)

• **WANG, Cong**
Shanghai 200032 (CN)

• **TANG, Yong**
Shanghai 200032 (CN)

• **ZHANG, Yuliang**
Shanghai 200032 (CN)

• **XIA, Chun-an**
Shanghai 200032 (CN)

(74) Representative: **Körner, Peter et al**
Thömen & Körner
Zeppelinstrasse 5
30175 Hannover (DE)

(54) **CATALYST FOR POLYMERIZATION OR COPOLYMERIZATION OF OLEFINS, PREPARATION AND USE OF THE SAME**

(57) Catalysts and catalyst systems useful for the olefin polymerization and copolymerization, and their synthesis procedure and usage are disclosed. These catalyst are a kind of novel complexes formed by transition metal from group 3 to group 11 and multidentate ligand, wherein the catalysts have the following formula:





Fig. 1

EP 1 426 385 A1


Description

FIELD OF THE INVENTION

[0001] This invention provides a new class of catalysts (catalyst systems) used for olefin polymerization and copolymerization, their synthesis and utility as homogeneous catalysts (used directly without supporting) or as heterogeneous catalysts (used after supported on the solids materials such as macromolecular materials, silica, alumina, magnesium chloride etc. or used as catalyst supported on polymer). The catalyst based on group 3 to group 11 transition metal complexes of multidentate ligands.

BACKGROUND OF THE INVENTION

[0002] Since the discovery of the Ziegler-Natta catalyst in 1950s, highly active MgCl_2 -supported Ti catalysts prove to have excellent properties. (N. Kashiwa etc., US-3642746, 1968) and are used for the manufacture of HDPE, LLDPE and i-PP. However, these catalysts are difficult to control the structure and physical properties of the polymer by changing the steric hindrance and electronic effect of the catalyst effectively. The metallocene single-site is found to be excellent for the controllable synthesis of the bulk materials (W. Kaminsky etc., *Angew. Chem. Int. Ed. Engl.* 1980, 19, 390; H. H. Brintzinger etc. *Angew. Chem. Int. Ed. Engl.* 1995, 34, 1143; Ishihara, Takeshi, JP 07268029; Exxon Co. Int., WO 9600243. WO 961 1960, WO 9400500, WO 9506071). Several single-site non-metallocene catalysts with ligands having N, O, P atom etc. have also been developed since 1995 (M. S. Brookhart etc., WO 9623010, WO 98/30612, WO 99/02472; V. C. Gibson etc., WO 99/12981, WO 98/27124; D. H. McConville etc., WO 2000/069922; R. H. Grubbs etc., WO 98/42664, WO 98/42665; Terunori Fujita etc., WO 99/54364). Selected catalysts are showed as follows:



[0003] To date, few reports appeared on the polymerization of olefins by non-metallocene titanium (IV) trichloride and zirconium (IV) trichloride complexes based on the single anion ligands, Nagy S. group reported the synthesis of 8-hydroxyl Quinoline titanium (IV) complex, which showed high activity in ethylene polymerization (Nagy S. etc. WO 9634021). A. Otero group reported the catalyst h was highly active in ethylene polymerization and gave high molecular weight PE and broad molecular weight dispersity (*Organometallics*, 2001, 20, 2428-2430).


AIM OF THE INVENTION

[0004] The aim of the invention is to provide a new class of olefin polymerization and copolymerization catalysts (catalyst systems), which are the complexes based on group 3 to group 11 transition metals and multidentate ligands.

[0005] The aim of the invention is to provide the synthesis of the catalysts, including the synthesis of the ligands and the catalysts by contacting of the ligands with transition metals.


[0006] The aim of the invention is to provide the usage of the said catalysts and the catalyst systems, the said catalysts or the catalyst systems can be used as homogeneous (used directly without support) or heterogeneous catalysts (used after supported on the solids materials such as macromolecular materials, silica, alumina, magnesium chloride etc. or used as catalyst supported on polymer) to catalyze the polymerization of ethylene, α -olefin, and monomers containing functional group. The said polymerization means the homopolymerization, oligomerization and copolymerization of the monomers. It also provides the process of preparing the homopolymers, oligomers and copolymers of the said olefin monomers.

[0008] The catalysts may be synthesized easily in high yield, they can be used to catalyze the homopolymerization (including oligomerization) and copolymerization of ethylene, α -olefin, olefins containing functional group; The catalyst system showed special characters in catalyzing the polymerization of ethylene: high activity even under the atmosphere pressure with a wide temperature range (-30°C - 150°C) and Al ratio(Al/Cat= 10-3000:1). It also showed high activity in the presence of different co-catalysts. Another outstanding character of the catalyst is that the activity is still higher (10^5 g PE/mol Ti. h. atm) when Al/Cat is lowered to 100:1 even to 10:1. The temperature at which the ethylene polymerization is suitable for commercial use; the molecular weight distribution is narrow and the Mw of the polymer is controllable, the branching can be tuned from 0 to 100/1000C; the content of the comonomer is adjustable. All of the distinguished characters make the catalysts suitable for commercial use. The structure of the catalyst is showed below:




[0009] The present invention provides a new class of olefin polymerization and copolymerization catalyst (catalyst systems) and its preparation and usage in catalyzing the homopolymerization (including the oligomerization and copolymerization) of ethylene, α -olefin and olefins containing functional group. It also provides the usage and the condition of polymerization about the said catalysts. The catalysts provided in this invention are group 3 to group 11 transition metal complexes of multidentate ligands.


[0010] The olefin polymerization and copolymerization catalysts provided in this invention are the transition metal complexes showed below (formula I):




[0011] A detailed representation of the catalyst is showed as formula IA and IB:



[0012] Formula IA is represented by formula IA-1~IA-4 in detail:



[0013] Formula IB is represented by formula IB-1~IB-4 in detail:



Wherein:

m is 1, 2 or 3;

q is 0 or 1;

d is 0 or 1;

M is group 3 to group 11 transition metal, preferable to Ti (IV), Zr (IV), Hf (IV), Cr (III), Fe (II, III), Co (II), Ni (II), and Pd (II);

n is 1, 2, 3 or 4;

X represent the group including halogen atom, H, hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀, group containing oxygen atom, group containing nitrogen atom, group containing sulfur atom, group containing boron atom, group containing aluminium atom, group containing phosphorus atom, group containing silicon, group containing germanium atom or group containing selenium atom, each X in the formula may be same or different, and they may link to one another to form covalent bond or to form a ring;

[0014] The said halogen atom include F, Cl, Br, I;

[0015] The absolute value of total negative charges of all ligands in the formula is the same as the absolute value of positive charges of M in the formula; the ligands include each X and multidentate ligands.

A is O, S, Se,



-NR²³R²⁴, -N(O)R²⁵R²⁶



-PR²⁸R²⁹, -P(O)R³⁰R³¹, sulfonyl, sulfoxidyl, -Se(O)R³⁹:

B is group containing nitrogen atom, group containing phosphorus atom or hydrocarbyl of C₁-C₃₀;

D is O, S, Se, group containing nitrogen atom of C₁-C₃₀, group containing phosphorus atom of C₁-C₃₀, sulfonyl, sulfoxidyl,



-N(O)R²⁵R²⁶,



-P(O)R³²(OR³³), wherein, O, S, Se, N, P are coordinate atoms;

E is group containing nitrogen atom, group containing oxygen atom, group containing sulfur atom, group containing selenium atom, group containing phosphorus atom, and N, O, S, Se, P are coordinate atoms;

F is group containing nitrogen atom, group containing oxygen atom, group containing sulfur atom, group containing selenium atom, group containing phosphorus atom, and N, O, S, Se, P are coordinate atoms;

G is inert group, including hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀ or inert functional group;

Y, Z respective are groups containing nitrogen atom, groups containing sulfur atom, groups containing oxygen atom, groups containing phosphorus atom, groups containing selenium atom such as -NR²³R²⁴, -N(O)R²⁵R²⁶, -PR²⁸R²⁹, -P(O)R³⁰R³¹, -OR³⁴, -SR³⁵, -S(O)R³⁶, SeR³⁸, -Se(O)R³⁹;

→ refers to single bond or double bond:

..... refers to coordinate bond, covalent bond or ionic bond;

— Refers to covalent bond or ionic bond;

R¹, R², R³, R⁴, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹², R¹³, R¹⁴, R¹⁵, R¹⁶, R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³, R²⁴, R²⁵, R²⁶, R²⁷, R²⁸, R²⁹, R³⁰, R³¹, R³², R³³, R³⁴, R³⁵, R³⁶, R³⁸, R³⁹ are H, hydrocarbyl of C₁-C₃₀, halogen, substituted hydrocarbyl of C₁-C₃₀ among which the halogen substituted hydrocarbyl are preferred, such as —CH₂Cl, —CH₂CH₂Cl or inert functional group. These groups may be same or different and the adjacent groups such as R¹ with R², R³, R³ with R⁴, R⁶, R⁷, R⁸, R⁹ and R²³ with R²⁴ or R²⁵ with R²⁶ may form a covalent bond or to form a cycle;

R⁵ is lone pair electron of nitrogen atom, H, hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀, group containing oxygen atom including hydroxyl, hydrocarbyloxy group -OR³⁴, hydrocarbyl containing -T-OR³⁴, group containing sulfur atom including -SR³⁵, -T-SR³⁵, group containing nitrogen atom including -NR²³R²⁴, -T-NR²³R²⁴, group containing phosphorus atom including -PR²⁸R²⁹, -T-PR²⁸R²⁹, -T-P(O)R³⁰R³¹; When R⁵ is group containing oxygen atom, group containing sulfur atom, group containing nitrogen atom, group containing selenium atom, group containing phosphorus atom, the N, O, S, P, Se atom in the group may coordinate with M.

[0016] T is hydrocarbyl of C₁-C₃₀ or substituted hydrocarbyl of C₁-C₃₀ may be inert functional group.

[0017] The catalyst system provided in this invention means the system containing the said catalyst and it comprises six classes including simply ① or ④ or ① supported on ② or contacting ① and ③ or ① and ③ supported on ② or contacting ③ and ④; ①, ②, ③ and ④ are described below:

① the catalyst showed in formula I;


② solid supports including macromolecular support materials, inorganic oxide support materials such as silica, alumina, titania, inorganic chloride support materials such as magnesium chloride, it also may be the mixtures of the said support materials;

③ the co-catalyst W;

④ catalyst supported on the polymer;

Preparation of the catalyst

[0018] In this invention, the catalyst is prepared in organic solvent by mixing the ligand (II) or the anion of the ligand with transition metal complex (III) in mole ratio 1:0.1~6 for 0.5~40 hours under the -78°C to reflux temperature, the reaction time has little effect on the result. The organic solvent may be THF, petroleum ether, toluene, CH₂Cl₂, CCl₄, ethyl ether, dioxane or 1,2-CH₂ClCH₂Cl etc..



Wherein:

q is 0 or 1;
d is 0 or 1;
A is O, S, Se,

-NR²³R²⁴, -N(O)R²⁵R²⁶,

-PR²⁸R²⁹, -P(O)R³⁰R³¹, sulfuryl, sulfoxidyl, -Se(O)R³⁹;

B is group containing nitrogen atom, group containing phosphorus atom or hydrocarbyl of C₁-C₃₀;
D is O, S, Se, group containing nitrogen atom of C₁-C₃₀, group containing phosphorus atom of C₁-C₃₀, sulfuryl, sulfoxidyl,

, -N(O)R²⁵R²⁶,

, -P(O)R³⁰R³¹, -P(O)R³²(OR³³), among them, O, S, Se, N, P are coordinate atoms;

E is group containing nitrogen atom, group containing oxygen atom, group containing sulfur atom, group containing selenium atom, group containing phosphorus atom, among them, N, O, S, Se, P are coordinate atoms;


G is inert group, including hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀ or inert functional group;

→ represent single bond or double bond;


— represent covalent bond or ionic bond;

R¹, R², R³ are H, hydrocarbyl of C₁-C₃₀, halogen, substituted hydrocarbyl of C₁-C₃₀ among which the halogen substituted hydrocarbyl are preferred, such as —CH₂Cl, —CH₂CH₂Cl or inert functional group. These groups may be same or different and the adjacent groups may form a covalent bond or to form a cycle;

[0019] Ligand (II) may be described by formula IIA and IIB as showed below:



[0020] Formula IIA and IIB may be represented by formula (IIA-1~IIA-4) and (IIB-1~IIB-4) in detail:



Wherein:

q is 0 or 1;

d is 0 or 1;

A is O, S, Se,



-NR²³R²⁴, -N(O)R²⁵R²⁶,



-PR²⁸R²⁹, -P(O)R³⁰R³¹, sulfonyl, sulfoxidyl, -Se(O)R³⁹;

B is group containing nitrogen atom, group containing phosphorus atom or hydrocarbyl of C₁-C₃₀;

E is group containing nitrogen atom, group containing oxygen atom, group containing sulfur atom, group containing selenium, group containing phosphorus atom, among them, N, O, S, Se, P are coordinate atoms;

F is group containing nitrogen atom, group containing oxygen atom, group containing sulfur atom, group containing selenium, group containing phosphorus atom, among them, N, O, S, Se, P are coordinate atoms;

G is inert group, including hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀ or inert functional group;

Y, Z are group containing nitrogen atom, group containing sulfur atom, group containing oxygen atom, group containing phosphorus atom, group containing selenium atom such as -NR²³R²⁴, -N(O)R²⁵R²⁶, -PR²⁸R²⁹, -P(O)R³⁰R³¹, -OR³⁴, -SR³⁵, -S(O)R³⁶, SeR³⁸, -Se(O)R³⁹;

→ represent single bond or double bond;

— represent covalent bond or ionic bond;

R¹, R², R³, R⁴, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹², R¹³, R¹⁴, R¹⁵, R¹⁶, R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹, R²², R²³, R²⁴, R²⁵, R²⁶, R²⁷, R²⁸, R²⁹, R³⁰, R³¹, R³², R³³, R³⁴, R³⁵, R³⁶, R³⁸, R³⁹ are H, hydrocarbyl of C₁-C₃₀, halogen, substituted hydrocarbyl of C₁-C₃₀ among which the halogen substituted hydrocarbyl are preferred, such as —CH₂Cl, —CH₂CH₂Cl or inert functional group. These groups may be same or different and the adjacent groups such as R¹ with R², R³ with R⁴, R⁶, R⁷, R⁸, R⁹ and R²³ with R²⁴ or R²⁵ with R²⁶ may form a covalent bond or to form a ring;

R⁵ is lone pair electrons of nitrogen atom, H, hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀, group containing oxygen atom including hydroxy, hydrocarboxyl -OR³⁴, hydrocarbyl containing ethereal bond including -T-OR³⁴, group containing sulfur atom including -SR³⁵, -T-SR³⁵, group containing N including -NR²³R²⁴, -T-NR²³R²⁴, group containing P including -PR²⁸R²⁹, -T-PR²⁸R²⁹, -T-P(O)R³⁰R³¹; When R⁵ is group containing oxygen atom, group containing sulfur atom, group containing nitrogen atom, group containing selenium atom, group containing phosphorus atom, the N, O, S, P, Se atom in the groups may coordinate with M.

[0021] T is hydrocarbyl of C₁-C₃₀ or substituted hydrocarbyl of C₁-C₃₀ or may be inert functional group.

[0022] The said "metal complex" can be represent by the formula (III):



Wherein:

g is 1, 2, 3, 4, 5 or 6;

M is group 3 to group 11 transition metal, preferable to Ti (IV), Zr (IV), Hf (IV), Cr (III), Fe (II, III), Co (II), Ni (II), Pd (II);

X is the group including halogen atom, H, hydrocarbyl of C₁-C₃₀, substituted hydrocarbyl of C₁-C₃₀, group containing oxygen atom, group containing nitrogen atom, group containing sulfur atom, group containing boron atom, group containing aluminium atom, group containing silicon atom, group containing germanium atom or group containing selenium atom, each X in the formula may be same or different, and they may link to one another to form covalent bond or to form a ring;

[0023] The said halogen atom include F, Cl, Br, I.

The Usage of the Catalyst—Reaction, Polymerization Process and the Polymer Product

[0024] The catalysts (catalyst system) provided in this invention may catalyze olefin polymerization as homogeneous catalyst (used directly without supporting) or heterogeneous catalyst (supported on macromolecular materials, silica, alumina, magnesium chloride etc. or the mixtures of several supports or used as catalyst supported on the polymer).

The said polymerization includes oligomerization, homopolymerization and copolymerization, and the catalysts (catalyst system) may be used by itself or in the presence of co-catalyst.

[0025] In the polymerization process, the polymerization temperature is preferable from about -100°C to about 200°C and the polymerization process provided in this invention at least includes contacting ④ with ① or contacting ④ with ⑤ or contacting ④ with ① supported on ② in certain order, ③ also may be involved in the process. ①, ②, ③,

④ and ⑤ are described below:

① the catalyst showed in formula (I);

② the solid supports;

- ③ the co-catalyst W;
- ④ olefin monomer;
- ⑤ the catalyst supported on the polymer.

[0026] In general, the catalyst system provided in the present invention may catalyze the polymerization of olefin monomers including ethylene, α -olefin, styrene, all kinds of olefinic acid and their derivatives, olefinic alcohol and their derivatives, dienes, cycloolefins etc.. The said α -olefins are the olefins of C_3 - C_{16} such as propene, 1-butene, 1-pentene, 1-hexene, 1-octene, 4-methyl-1-pentene etc. and the mixtures of them; the said cycloolefins are cyclopentene, cyclohexene, norbornene etc. and their derivatives. The term polymerization refers to the homopolymerization and copolymerization of the said monomers and the said homopolymerization includes the oligomerization.

[0027] The polymerization can be run in the liquid process, slurry process, gas process, loop reactor or other polymerization processes.

[0028] The polymerization process generally can be conducted in inert solvents such as alkanes, cycloalkanes or aromatic hydrocarbons. The said inert solvents prefer to but not limited to the hydrocarbon of C_1 - C_{12} such as propane, i-butane, pentane, 2-methylbutane, hexane, toluene, chlorobenzene and/or their mixtures.

[0029] The temperature at which the polymerization process conducted is from -50°C to 150°C , preferred 0°C to 120°C for higher activity and productivity.

[0030] The polymerization process is generally conducted from 0.1 to 10MPa, preferably 0.1 to 3 MPa for better operating parameter and superior polymer product.

[0031] The said co-catalyst W may be MAO, MMAO, EAO, BAO, LiR (R= alkane of C_1 - C_{10}), AlR_3 (R= alkane of C_1 - C_{10}), Lewis acid, LiR/Lewis acid (R= alkane of C_1 - C_{10}), Borane such as $\text{B}(\text{C}_6\text{F}_5)_3$ etc..

[0032] In the polymerization process, the catalyst and co-catalyst may be introduced in any sequence and the mole ratio of the catalyst and the cocatalyst may be changed from 1:1 to 1:5000, preferably 1:10 to 1:2000 for higher activity and yielding polymer with superior morphology and the lower cost.

[0033] The polymerization process may be conducted in flask, autoclave, loop reactor or other types of reactors, in addition, the polymerization may be conducted in single reactor, single reactor, reactors in series or in parallel or in reactors with a combination, the reaction condition in each reactor may be the same or may be not.

Terms used in the invention are elucidated below:

[0034] The term "catalyst system" in this invention means the system comprising six classes including simply ① or ④ or ① supported on ② or contacting ① with ③ or contacting ① with ③ supported on ② in certain order or contacting ③ with ④; ①, ②, ③ and ④ are described below:

- ① the catalyst showed in formula I;
- ② solid support including macromolecular support materials, inorganic oxide support materials such as silica, alumina, titania, inorganic chloride support materials such as magnesium chloride, it also may be the mixtures of the said support materials;
- ③ the cocatalyst W;
- ④ catalyst supported on the polymer.

[0035] The "co-catalyst W" refers to a neutral Lewis acid, which can remove X^- from M to form $(\text{WX})^-$: when the produced $(\text{WX})^-$ is an anion with weak coordination ability, W can transfer hydrogen to the center metal. For instance, alkyl aluminoxane MAO or MMAO (modified MMAO); Also, one can use two compounds together, of which, one may transfer the alkyl or the hydrogen ion to the metal atom, such as alkyl aluminium compound preferably AlEt_3 , AlMe_3 , $\text{Al}(\text{i-Bu})_3$ and another one may remove X^- from M such as the sodium salt or silver salt: $\text{Na}[\text{B}(3,5-(\text{CF}_3)_2\text{C}_6\text{H}_3)_4]$, $\text{AgOSO}_2\text{CF}_3$, alkyl aluminium compounds or borane $\text{B}(\text{C}_6\text{F}_5)_3$ etc.

[0036] The weak-coordinating anions are the anions that are relatively non-coordinated with the metal, the ability of the anions has been discussed in the literature (W. Beck, et al., *Chem. Rev.*, **1988**, *88*, 1405-1421; S. H. Strauss, *Chem. Rev.*, **1993**, *93*, 927-942) and the references therein, for the instance, $(\text{R}^{41})_3\text{AlX}^-$, $(\text{R}^{41})_2\text{AlX}_2^-$, $(\text{R}^{41})\text{AlX}_3^-$, SbF_6^- , PF_6^- , BF_4^- , $(\text{C}_6\text{F}_5)_4\text{B}^-$, $(\text{R}_f\text{SO}_2)_2\text{N}^-$, CF_3SO_3^- , $((3,5-(\text{CF}_3)_2\text{C}_6\text{H}_3)_4\text{B}^-$;

[0037] The hydrocarbon refers to the alkanes of C_1 - C_{30} , cycloalkanes of C_2 - C_{30} containing alkyne, aromatic hydrocarbons of C_6 - C_{30} , hydrocarbon with fused rings of C_8 - C_{30} or heterocyclic compounds of C_4 - C_{30} ;

[0038] The substituted hydrocarbon is the hydrocarbon having one or more substituted groups which are inert, this means the groups wouldn't interfere with the process by coordinating with the metal atom. If not stated otherwise, it is preferred the halogen substituted groups of C_1 - C_{30} or the halogen substituted aromatic hydrocarbons of C_6 - C_{30} including the hydrocarbon with fused rings of C_8 - C_{30} or heterocyclic of C_4 - C_{30} ;

[0039] The inert functional groups in this invention are functional groups other than hydrocarbons and substituted

hydrocarbons which are inert and don't interfere with the process. The functional groups herein include halogen (F, Cl, Br, I), groups containing oxygen atom, groups containing nitrogen atom, groups containing silica atom, groups containing germanium atom, group containing sulfur atom or group containing stannum atom such as ether (-OR³⁴ or -TOR³⁵), ester of C₁-C₁₀, amine of C₁-C₁₀, alkoxyl of C₁-C₁₀, nitril etc. The coordination ability of these inert functional groups with the metal atom is weaker than the groups of A, D, E, F, Y, Z in the formula (I), and coordination group A, D, E, Y, Z with the metal can not be substituted by these inert groups.

The groups containing nitrogen atom are



-NR²³R²⁴, -T-NR²³R²⁴, -N(O)R²⁵R²⁶;

The groups containing phosphorus atom are



-PR²⁸R²⁹, -P(O)R³⁰R³¹, -P(O)R³²(OR³³);

The groups containing oxygen atom are hydroxyl, hydrocarboxyl such as -OR³⁴, -T-OR³⁴;

The groups containing sulfur atom are -SR³⁵, -T-SR³⁵, -S(O)R³⁶, -T-SO₂R³⁷;

The groups containing selenium atom are -SeR³⁸, -T-SeR³⁸, -T-Se(O)R³⁹;

The groups containing boron atom are BF₄⁻, (C₆F₅)₄B⁻, (R⁴⁰BAr₃)⁻etc.;

The groups containing aluminium atom are alkyl aluminium compound, AlPh₄⁻, AlF₄⁻, AlCl₄⁻, AlBr₄⁻, AlI₄⁻, R⁴¹AlAr₃⁻;

The groups containing silicon atom are -SiR⁴²R⁴³R⁴⁴, -T-SiR⁴⁵;

The groups containing germanium are -GeR⁴⁶R⁴⁷R⁴⁸, -T-GeR⁴⁹;

The groups containing stannum atom are -SnR⁵⁰R⁵¹R⁵², -T-SnR⁵³, -T-Sn(O)R⁵⁴;

T is hydrocarbyl of C₁-C₃₀ or substituted hydrocarbyl of C₁-C₃₀ or inert functional group.

[0040] Alkyl aluminium compound is the compound that substituents bound to aluminium atom directly and among them at least one group is alkyl. Such as MAO, MMAO (modified MAO), AlEt₃, AlMe₃, Al(i-Bu)₃;

R²², R²³, R²⁴, R²⁵, R²⁶, R²⁷, R²⁸, R²⁹, R³⁰, R³¹, R³², R³³, R³⁴, R³⁵, R³⁶, R³⁷, R³⁸, R³⁹, R⁴⁰, R⁴¹, R⁴², R⁴³, R⁴⁴, R⁴⁵, R⁴⁶, R⁴⁷, R⁴⁸, R⁴⁹, R⁵⁰, R⁵¹, R⁵², R⁵³, R⁵⁴ independently represents H, hydrocarbyl of C₁-C₃₀, halogen atom, substituted hydrocarbyl of C₁-C₃₀ or inert functional group. These groups may be same or different and the adjacent groups may form a covalent bond or to form a cycle;

DESCRIPTION OF THE FIGURE

[0041]

Figure 1 is the X-ray of compound J-1.

[0042] In summary, the present invention provides a new class of olefin polymerization and copolymerization catalysts (or catalyst systems), which is a new kind of multidentate complexes based on group 3 to group 11 transition metals. The present invention also provides the synthesis of the ligands and the catalysts and their usage in the olefin polymerization process. The catalysts are synthesized by contacting the ligand with the complex (III) in organic solvent. The catalyst provided in the invention may be used by itself or in the presence of co-catalyst as a homogeneous (used directly without supporting) or as a heterogeneous system (supported on macromolecular materials, inorganic oxide support materials such as silica, alumina, inorganic chloride materials such as magnesium chloride, or the mixtures of the said supports or as catalyst supported on polymer) to catalyze the homopolymerization and copolymerization of olefin monomers such as ethylene, α -olefin, olefins containing functional groups etc..

Examples

[0043] The present invention can be explained in detail by the following examples, but not limited to these.

[0044] The following examples showed the different aspects of the invention. The examples provided include the synthesis of ligands, synthesis of metal complexes, polymerization process, polymerization conditions and polymer

produced. All manipulations including reaction, preparation and storage were performed under inert atmosphere using standard Schlenk techniques. Molecular weight and molecular weight distribution were determined by Waters model 150 GPC (differential refractive index detector) at 140°C and 1, 2-Dichlorobenzene as eluent, polystyrene as reference sample.

Example 1 to 20 showed the synthesis of some ligands.

Example 21 to 35 showed the synthesis of some catalysts.

Example 36 to 40 showed special catalytic character of system (A-1) in catalyzing the polymerization of ethylene: high activity is obtained even under the atmosphere pressure and wide temperature limit (-30°C-150°C) and broad range Al: Cat (Al/Cat= 10~3000:1), it also showed high activity in the presence of different co-catalysts. Another outstanding character about the catalyst is the activity higher than 10⁵ g PE/mol Ti. h. atm can be obtained when Al/cat is lowered to 100:1 even to 10:1. The temperature at which the ethylene polymerization is carried out is suitable for commercial use (40°C-80°C); the molecular weight disperse is narrow and the Mw of the polymer is controllable, and the branching can be tuned from 0 to 100 every 1000C; the content of the comonomer is adjustable. A ll of these distinguish characters make the catalysts be capable of applying to practice. Not only A-1 system but also the other systems all showed these distinguish characters in the polymerization process.

Example 41 to 54 showed the polymerization results catalyzed by early-transition metal complexes.

Example 55 to 58 showed olefin polymerization results catalyzed by late-transition metal complexes.


Example 59 to 72 showed the polymerization results of olefin monomers besides ethylene.

Example 73 showed the polymerization results catalyzed by the alkylated complexes.

Example 74 showed the ethylene polymerization by the heterogeneous catalysts.

Example 1 Synthesis of ligand L1

[0045] To a solution of 3, 5-di-*tert*-butyl salicylaldehyde 8.2 g (34.4 mmol) and (*o*-aminophenyl) diphenylphosphine 9.6 g (34.6 mmol) in anhydrous ethanol (50 ml) was added zeolite and a few drops of glacial acetic acid in a flask. After refluxing for 24h, filtered the zeolite, the filtrate was concentrated, cooled to room temperature to give the crude product. Recrystallization from ethanol/ether gave the ligand L1 as pale yellow crystals, 11.8 g (69%):




Anal. Found (calcd): C: 80.39 (80.29), H: 7.59 (7.35), N: 2.77 (2.84);

¹H NMR (300 MHz CDCl₃): δ 8.4 (s, CH=N), 7.4-6.8 (m, Aryl-H), 1.4 (s, *t*-Bu-H), 1.3 (s, *t*-Bu-H);
δ (³¹P)-13.63 (s).

Example 2 Synthesis of ligand L2

[0046] To a flask was added a solution of 3, 5-di-*tert*-butyl salicylaldehyde 2.34 g (10.0 mmol) and (*o*-aminophenyl) diphenylamine 2.3 g (8.8 mmol) in anhydrous ethanol of 100 ml. After refluxing 24 h, the resulting mixture was cooled to room temperature to give the product, then washing with cool ethanol for several times and dried to give ligand L2 as yellow crystals. 3.5g (81%).




Anal.: Found (Calcd): C: 83.19 (83.15), H: 7.60 (7.61), N: 5.87 (5.88);

^1H NMR (300 MHz CDCl_3): δ 13.6 (s, O-H), 8.6 (s, CH=N), 7.5-7.0 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 3 Synthesis of ligand L3

[0047] To a solution of 3, 5- di-*tert*-butyl salicylaldehyde 2.34 g (10.0 mmol) and 2,6-di-methylphenyl-2-aminophenylether 2.13 g (10.0 mmol) in anhydrous ethanol 50 ml was added to a flask of 250 ml. After refluxing for 20 h, the resulting mixture was cooled to room temperature to give the crude product, washing with anhydrous ethanol for several times, and drying to give ligand L3 as yellow crystals 2.9 g (81%).




L3

Anal.: Found (calcd): C: 80.86 (81.06), H: 8.13 (8.23), N: 3.23 (3.26);

^1H NMR (300 MHz CDCl_3): δ 14.0 (s, O-H), 8.86 (s, CH=N), 7.46-6.43 (m, Aryl-H), 2.17 (s, CH_3), 1.50 (s, t-Bu-H), 1.31 (s, t-Bu-H).

Example 4 Synthesis of ligand L4

[0048] To a solution of 3, 5- di-*tert*-butyl salicylaldehyde 2.8 g (12.0 mmol) and phenyl-2-aminophenylsulfide 2.01 g, (10.0 mmol) in 25ml anhydrous ethanol was added a few drops of glacial acetic acid. Refluxing and stirring for 2h, the resulting mixture was cooled to room temperature to give yellow green solid. Recrystallized to give ligand L4, 1.3 g (44.4%).




L4

Anal.: Found (Calcd): C: 77.70 (77.65), H: 7.50 (7.48), N: 3.38 (3.35);

^1H NMR (300 MHz CDCl_3): δ 13.3 (s, O-H), 8.6 (s, CH=N), 7.45-7.11 (m, Aryl-H), 1.47 (s, t-Bu-H), 1.32 (s, t-Bu-H).

Example 5 Synthesis of ligand L5

[0049] To a solution of 3, 5- di-*tert*-butyl salicylaldehyde 2.8g (12.0 mmol) and perfluorophenyl-2-aminophenylether 2.75g (10.0 mmol) in anhydrous ethanol of 25 ml was added a few drops of glacial acetic acid. Refluxing and stirring until the substrate disappeared, the resulting mixture was cooled and filtered to give the crude product. Recrystallized to give product L5, 3.5 g (71%).




L5

Anal. : Found (Calcd): C: 65.70 (65.98), H: 5.40 (5.33), N: 3.01 (2.85);

^1H NMR (300 MHz CDCl_3): δ 13.1 (s, O-H), 8.7 (s, CH=N), 7.4-7.1 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 6 Synthesis of ligand L6


[0050] To a solution of 3, 5- di-*tert*-butylsalicylaldehyde 3.4g (14.0 mmol) and 8-aminoquinoline 2.3g (16.0 mmol) in anhydrous ethanol of 100 ml was added a few drops of glacial acetic acid. Refluxing and stirring for 24h, the product was purified by column chromatography to give ligand L6, 2.31g (64%).



Anal.: Found (Calcd): C: 80.25 (79.96), H: 7.88 (7.83), N: 7.75 (7.77);
¹H NMR (300 MHz CDCl₃): 14.0 (s, O-H), 8.9 (s, CH=N), 9.0 (d, pyridine-2), 8.2 (d, pyridine-4), 7.6 (t, pyridine-3), 7.7-7.4 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.4 (s, t-Bu-H).

Example 7 Synthesis of ligand L7


[0051] To a solution of 3, 5- di-*tert*-butyl salicylaldehyde 2.0 g (8.5mmol) and 2-aminomethylpyridine 0.92g (8.5 mmol) in CH₂Cl₂ of 25 ml was added anhydrous MgSO₄ at room temperature, stirring for 20 h and the mixture was filtered. The solvent was removed and the crude product was purified by column chromatography to give ligand L7, 1.21 g (44.4%).



Anal.: Found (Calcd): C: 77.70 (77.57), H: 8.85 (8.98), N: 8.59 (8.60);
¹H NMR (300 MHz CDCl₃): δ 13.6 (s, O-H), 8.6 (m, 2H), 7.69-7.14 (m, Aryl-H), 4.93 (s, -CH₂-), 1.45 (s, t-Bu-H), 1.32 (s, t-Bu-H).

Example 8 Synthesis of ligand L8


[0052] L8 was prepared by the same procedure as the ligand L1, but the reactant was replaced by 2-hydroxyl 5-nitrobenzaldehyde and *O*-aminophenyldiphenylphosphine.



Anal. Found (Calcd) C: 70.77 (70.42), H: 4.50 (4.49), N: 6.45 (6.57);
¹H NMR (300 MHz CDCl₃): δ 8.0 (s, CH=N), 7.7-6.6 (m, Aryl-H).


Example 9 Synthesis of ligand L9

[0053] To a solution of ligand L1 0.98g (2.0mmol) in methol (10ml) was added NaBH₄ 0.14g (4.0mmol) in methol (5ml) under the nitrogen atmosphere, the mixture was stirred for additional 30 min, then quenched with ice water. The crude product was purified by column chromatography to give the L9, 940mg (94.8%)



Anal: Found (Calcd): C: 79.87 (79.97), H: 7.89 (7.73), N: 2.81 (2.82);
 ^1H NMR (300 MHz CDCl_3): 7.74-6.78 (m, 16H), 4.15 (s, 2H), 1.40 (s, t-Bu-H), 1.38 (s, 9H).


[0054] The ligands containing imine can be reduced or alkylated by the similar procedure, such as L10:



Anal.: Found (Calcd): C: 77.68 (77.28), H: 7.85 (7.93), N: 3.03 (3.34);
 ^1H NMR (300 MHz CDCl_3): δ 7.6-7.0 (m, Aryl-H), 5.1 (br s), 4.33 (s, CH_2), 1.33 (s, t-Bu-H), 1.31 (s, t-Bu-H).

Example 10 Synthesis of ligand L11


[0055] To a solution of (o-aminophenyl) diphenylamine 2.77g (10.0mmol) and compound (h) 3.92g (12.0mmol) in ethanol (15ml), zeolite and a few drops of acetic acid were added to the mixture, refluxing and heating for 3h, remove the solvent and the crude product was purified by column chromatography of silica gel to give L11.



Anal.: Found (Calcd.): C: 81.00 (81.02), H: 7.43 (7.55), N: 2.51 (2.62);
 ^1H NMR (300 MHz CDCl_3): 7.6-6.9 (m, 17H), 5.36 (s, 1H), 2.10 (s, 3H), 1.44 (s, t-Bu-H), 1.38 (s, 9H, 9H).

Example 11 Synthesis of ligand L12

[0056] To a solution of m-CBPA 650mg (0.31 mmol) in CH_2Cl_2 5ml was added L4 125mg (0.3mmol) in the solution of CH_2Cl_2 10ml at temperature of 0-5°C. The resultant mixture was stirred for additional 1h under the temperature of 0-5°C. The crude product was purified by column chromatography to give L12, 730mg (57.3%).




Anal.: Found (Calcd) C: 74.77 (74.79), H: 7.20 (7.21), N: 3.33 (3.23);

^1H NMR (300 MHz CDCl_3): 11.6 (s, O-H), 8.2 (s, $\text{CH}=\text{N}$), 8.0-7.0 (m, Aryl-H), 1.35 (s, t-Bu-H), 1.28 (s, t-Bu-H).

Example 12 Synthesis of ligand L13

[0057] A solution of O-aminophenyl diphenylphosphine in benzene can give O-aminophenyl diphenyloxyporphine quantitatively under the effect of H_2O_2 (30%). By the same procedure as ligand L1, L13 was prepared and purified by column chromatography, 560mg (64%).




Anal.: Found (Calcd) C: 77.87 (77.77), H: 7.14 (7.12), N: 2.71 (2.75).

^1H NMR (300 MHz CDCl_3): 11.7 (s, O-H), 8.2 (s, $\text{CH}=\text{N}$), 7.75-7.0 (m, Aryl-H), 1.33 (s, t-Bu-H), 1.28 (s, t-Bu-H).

Example 13 Synthesis of ligand L14

[0058] To a solution of phenyl-2-aminophenylsulfide 2.01g (10.0mmol) was added concentrated HCl 5ml and H_2O 10ml in a flask of 100ml, the solution of NaNO_2 0.76g (11.0mmol) in the H_2O 2.5ml was slowly added to the mixture. The mixture was stirred at temperature of 0°C for 2h to give diazonium salt. In another flask, to 2,4-di-*tert*-butylphenol 2.17g (10.5mmol) and the solution of NaOH 0.4g in H_2O 5ml was added the solution of Na_2CO_3 2.65g in H_2O 10ml slowly. At 0°C , added dropwise the diazonium salt to the anionic solution. The mixture was stirred for 3h at 0°C and warmed to room temperature, then filtered; the solid was recrystallized to give L14, 3.1g (75%).




Anal.: Found (Calcd) C: 74.70 (74.60), H: 7.11 (7.22), N: 6.56 (6.69);

^1H NMR (300 MHz CDCl_3): δ 13.3 (s, OH), 7.8-7.1 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 14 Synthesis of ligand L15


[0059] To the solution of L9 6.2g (12.5 mmol) in CH_2Cl_2 was added H_2O_2 20ml (30%). stirred quickly for 4h, separated the solvent, the organic layer was condensed to give ligand L15 quantitatively.



Anal.: Found (Calcd) C: 77.48 ((77.47), H: 7.29 (7.49), N: 3.03 (2.74);
¹H NMR (300 MHz CDCl₃): δ 7.7-6.7 (m, Aryl-H), 4.3 (d, CH₂N), 1.28 (s, t-Bu-H).

Example 15 Synthesis of ligand L16


[0060] To a mixture of NaH (4.0 mmol) and ligand L15 1.02 g (2.0 mmol) at -78°C, was added a solution of THF (30 ml). The mixture was warmed to room temperature and stirred for an additional 2h, then CH₃I (0.23 ml, 4.0 mmol) was added. The mixture was stirred for an additional 2h, Then distilled water was added and extracted by CH₂Cl₂, organic layer was dried by anhydrous Na₂SO₄, removed the solvent, the crude product was purified by column chromatography to give L16.



Anal.: Found (Calcd): C: 77.75 ((77.89), H: 7.88 (7.84), N: 2.69 (2.60);
¹H NMR (300 MHz CDCl₃): δ 7.7-6.9 (m, Aryl-H), 4.3 (s, CH₂), 3.6 (s, OMe), 2.2 (s, Me), 1.3(s, t-Bu-H), 1.2 (s, t-Bu-H).

Example 16 synthesis of ligand L17


[0061] To the solution of ligand L16 537mg (1.0mmol) in toluene was added HSiCl₃ 0.5ml (5.0mmol) at 0°C. After refluxing and stirring overnight, cooled to room temperature, added ether 40ml and saturated aqueous of NaHCO₃ 15ml, filtered and removed the solvent, the crude product was purified by column chromatography to give L17.




Anal. : Found (Calcd) C: 80.41 (80.270, H: 8.15 (8.08), N: 2.51 (2.67);
¹H NMR (300 MHz CDCl₃): δ 7.5-6.8 (m, Aryl-H), 4.2 (s, CH₂), 3.7 (s, OMe), 2.5 (s, NMe), 1.5 (s, t-Bu-H), 1.2 (s, t-Bu-H).

Example 17

[0062] L18, L19, L20, L28, L29, L30, L31, L32, L33, L34 were synthesized by the same procedure as L1.






[0063] Part of analysis results of L18- L34:

Anal., Found (Calcd); ¹H NMR, 300 MHz CDCl₃

L18: C: 77.84 (77.95), H: 5.31 (5.400, N: 7.66 (7.90);
8.1 (s, CH=N), 7.4-6.2 (m, Aryl-H), 1.9 (broad s, N-H).
L19: C: 83.75 (84.00), H: 5.38 (5.06), N: 2.87 (2.51);
13.5 (s, OH), 8.4 (s, CH=N), 8.9-7.0 (m, Aryl-H);
L20: C: 63.91 (63.89), H: 5.13 (5.16), N: 2.73 (2.76);
13.9 (s, OH), 8.3 (s, CH=N), 8.8-7.0 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, t-Bu-H);
L28: 8.3 (s, CH=N), 7.6-6.9 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (PMe);
L29: 8.3 (s, CH=N), 7.5-6.9 (m, Aryl-H), 3.0 (s, CH₂), 1.4 (s, t-Bu-H), 1.3 (s, t-Bu-H);
L30: 8.4 (s, CH=N), 8.3-7.1 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (s, Me);
L31: 8.4 (s, CH=N), 7.9-6.6 (m, Aryl-H), 1.31 (s, t-Bu-H), 1.29 (s, t-Bu-H);
L32: 9.3 (s, CH=N), 8.0-6.9 (m, Aryl-H);
L33: 13.2 (s, OH), 8.6 (s, CH=N), 7.6-7.1 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.35 (s, t-Bu-H);
L34: C: 78.85 (79.00), H: 7.85 (7.84), N: 8.33 (8.38).

Example 18 Synthesis of ligand L21


[0064] To a solution of ligand **L10** 490mg (1.0 mmol) in THF (5 ml) at -78°C, was added NaH (1.0 mmol) in 5 ml of THF. The resulting solution was allowed to warm to room temperature and stirred for 2h, and then a solution of Me₃SiCl (1.0 mmol) in 5 ml of THF was slowly added to the said solution. Refluxing 2hr and the solution was added to NaH (1 mmol) in THF of 5 ml, refluxing 10h, and cooled to room temperature. To the solution was added aqueous HI (44%), after refluxing and stirring for 12h, stopped the reaction and the crude product was purified by column chromatography to give **L21**.



Anal.: Found (Calcd) C: 80.25 (80.13), H: 7.88 (7.91), N: 2.75 (2.73).
¹H NMR (CDCl₃): 7.7-6.8 (m, Aryl-H), 4.0 (s, 2H), 2.5 (s, 3H), 1.4 (s, 9H), 1.3 (s, 9H).

Example 19 Synthesis of ligand L22

[0065] To a solution of ligand **L10** (838 mg, 2.0 mmol) in THF of 10 ml at -78°C, was added a solution of NaH (88 mg, 2.0 mmol) in THF of 5 ml, the mixture was allowed to warm to room temperature and stirred for an additional 1h, then CH₃I was slowly added to the system, Stopped the reaction after refluxing 10h, filtered and dried with anhydrous Na₂SO₄, filtered and removed the solvent, a few petroleum ether was added to give **L22** (72%).



Anal. : Found (Calcd) C: 77.25 (77.55), H: 8.18 (8.14), N: 3.35 (3.23);
¹H NMR (CDCl₃): 7.5-6.7 (m, Ary-H), 5.3 (br s, NH), 4.34 (s, 2H), 3.7 (s, 3H), 1.4 (s, t-Bu-H), 1.2 (s, t-Bu-H).

Example 20 Synthesis of ligand L27


[0066] To a solution of ligand L9 (6.2 g, 12.5 mmol) in CH₂Cl₂, was added H₂O₂ of 20 ml (30%), stirred quickly for 4h, separated the solvent, organic layer was condensed to give ligand L23 quantitatively.

[0067] To a solution of ligand L23 (509 mg, 1.0 mmol) in THF of 15 ml at -78°C, was added a solution of NaH (1.0 mmol) in THF of 5 ml, the mixture was allowed to warm to room temperature and stirred for an additional 2h, then a solution of Me₃SiCl (0.33 ml, 2.5 mmol) in THF of 15 ml was added to the anionic solution, refluxing 2h. The crude product was purified by column chromatography to give L24 (350 mg, 60%).

[0068] To a solution of ligand L24 (583 mg, 1.0 mmol) in THF of 15 ml at -78°C, was added a solution of NaH (1.0 mmol) in THF of 5 ml, the mixture was allowed to warm to room temperature, after stirring for an additional 2h, a solution of Me₂NCH₂CH₂Cl·HCl (144 mg, 1.0 mmol) was added to the anionic solution, refluxing 2h. The crude product was purified by column chromatography to give L25.

[0069] To a solution of ligand L25 (292 mg, 0.5 mmol) in THF of 10 ml, was added aqueous solution of HI (44%), refluxing for 12h. The crude product was purified by column chromatography to give L26.


[0070] L27 was prepared by the same method as L17.




[0071] Anal.: Found (Calc.) for L27 : C: 78.35 (78.41), H: 8.37 (8.36), N: 5.06 (4.94);
¹H NMR (300 MHz CDCl₃): 7.7-6.7 (m, Aryl-H), 3.9 (s, 2H), 2.6 (t, 2H), 2.2 (t, 2H), 1.9 (s, 3H), 1.4 (s, 9H), 1.3 (s, 9H).

Example 21 Synthesis of complex A-1

[0072] A solution of ligand L1 (740.5 mg, 1.5 mmol) in THF of 10 ml was added to KH (60 mg, 1.5 mmol) in THF of 10 ml at 0°C, stirred for an additional 1 h at room temperature. After the solvent was removed under vacuum, 30 ml of toluene was added to the residue, and then a solution of TiCl₄ 0.20 ml (0.18 mmol) in toluene (30 ml) was added drop wise to the said solution at room temperature, the mixture was stirred for 3h at room temperature. The solvent was removed under vacuum, the crude product was dissolved in CH₂Cl₂ (40 ml), centrifugalizing, and the organic layer was removed the solvent under vacuum to give orange red crude product, washed with hexane, toluene/hexane to give orange red solid 760 mg (78.3%).



Anal. Found (Calcd.) C: 60.36 (61.27), H: 6.01 (5.45), N: 2.01 (2.16);
¹H NMR (300 MHz CDCl₃): δ 8.2 (s, CH=N), 7.8-7.0 (m, Aryl-H), 1.51 (s, t-Bu-H), 1.34 (s, t-Bu-H). Complex A-1 isomerized under the action of dry hydrochloric to give complex J-1:



[0073] Table 1 and Figure 1, give the X-ray analysis of Complex J-1.


Table 1.

bond length and bond angle			
Ti-O	1.798(4)	N-C(6)	1.447(7)
Ti-Cl(1)	2.2583(19)	N-C(7)	1.522(6)
Ti-Cl(4)	2.279(2)	Cl(1)-Ti-Cl(4)	98.46(8)
Ti-Cl(2)	2.3720(18)	Cl(1)-Ti-Cl(2)	94.45(7)
Ti-Cl(3)	2.4119(19)	Cl(4)-Ti-Cl(2)	91.07(7)

Anal. Found (Calcd.) C: 58.31 (58.01), H: 5.28 (5.31), N: 2.02 (2.05); X-ray: See Figure 1.

Example 22 Synthesis of complex A-2

[0074] A solution of ligand L2 (476 mg, 1.0 mmol) in 15 ml of THF was added to KH 43 mg (1.1 mmol) in 15 ml of THF slowly at -78°C, stirred for 3h at room temperature. The solvent was removed under vacuum, following 40 ml of toluene was added to the residue, the solution was added drop wise to a solution of TiCl₄ 0.11 ml (1.0 mmol) in 40 ml of toluene at 50°C, stirred for additional 3h at 50°C, centrifugalizing and the organic layer was removed the solvent to give the crude product, recrystallized from CH₂Cl₂/hexane to give complex A-2, 380 mg (60%).




Anal. Found (Calc.) C: 62.05 (62.93), H: 5.03 (5.60), N: 7.25 (7.60);
¹H NMR (300 MHz CDCl₃): δ 8.3 (s, CH=N), 7.7-6.9 (m, Aryl-H), 1.6 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 23 Synthesis of complex B-1

[0075] A solution of ligand L1 300 mg (0.6 mmol) in 10 ml of THF was added drop wise to a solution of NaH (0.6


mmol) in 10 ml of THF at 0°C, stirred for 1h at room temperature, the solution was added to a solution of $\text{ZrCl}_4 \cdot 2\text{THF}$ 261.7 mg (0.6 mmol) in 15 ml of THF dropwise, stirring at 0°C for 0.5h then refluxing 7h, the solvent was removed in vacuum, the mixture was dissolved in 20 ml of CH_2Cl_2 , centrifugalizing and the organic layer was concentrated, cooled to give pale yellow crude product, recrystallized from CH_2Cl_2 /hexane to give complex B-1, 97.8mg (23.6%).



Anal. Found (Calc.) C: 56.91 (57.43), H: 5.24 (5.11), N: 2.23 (2.03), Cl: 15.62 (15.41).
 ^1H NMR (300 MHz CDCl_3): δ 8.3 (s, CH=N), 7.8-7.0 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 24 Synthesis of complex B-2


[0076] A solution of ligand L2 (476 mg, 1.0 mmol) in 50 ml of THF, was added drop wise to a suspension of KH (43 mg, 1.1 mmol) in 15 ml of THF at -78°C, stirred for 3h at room temperature. The solution was added drop wise to a solution of $\text{ZrCl}_4 \cdot 2\text{THF}$ (1.0 mmol) in 15ml of THF, refluxing 10h, the solvent was removed under vacuum, the residue was dissolved completely in 20 ml of CH_2Cl_2 , centrifugalizing and the organic layer was concentrated, a few drops of hexane was added to the mixture, cooled to give crude product, the crude product was recrystallized to give complex B-2, 215 mg (32%).




Anal. Found (Calc.) C: 57.91 (58.87), H: 5.04 (5.24), N: 4.23 (4.16), Cl: 15.31 (15.80);
 ^1H NMR (300 MHz CDCl_3): δ 8.4 (s, CH=N), 8.0-6.9 (m, Aryl-H), 1.6 (s, t-Bu-H), 1.3 (s, t-Bu-H).

Example 25

[0077] A-3, A-4, A-5, A-6, A-7, A-9, A-11, A-13, A-14, A-18, A-19, A-20, A-21, A-28, A-29, A-30, A-31, A-32, A-33, A-34 were synthesized as the said general procedure of A-1.





The following are part of analysis results: (Anal: Found (Calcd.); ^1H NMR, 300 MHz CDCl_3)

A-3

C: 59.04 (59.76), H: 5.58 (5.88), N: 2.26 (2.40);
 δ 8.8 (s, CH=N), 7.7-6.6 (m, Aryl-H). 2.5 (s, CH_3), 1.5 (s, t-Bu-H), 1.4 (s, t-Bu-H).

A-4

C: 57.04 (56.81), H: 5.11 (5.30), N: 2.13 (2.45);
 δ 8.9 (s, CH=N), 7.7-7.2 (m, Aryl-H), 1.5 (s, t-Bu), 1.3 (s, t-Bu-H).

A-5

C: 50.04 (50.30), H: 4.01 (3.91), N: 2.32 (2.17);
 δ 8.4 (s, CH=N), 7.4-7.0 (m, Aryl-H), 1.5 (s, t-Bu), 1.4 (s, t-Bu-H).

A-6

C: 56.74 (56.11), H: 5.48 (5.30), N: 5.26 (5.45);
 δ 9.0 (s, CH=N), 9.6 (d, pyridine-1H), 8.5 (d, pyridine-1H), 8.0 (q, Aryl-2H), 7.7 (m, Aryl-3H), 7.5 (d, Aryl-1H), 1.5 (s, t-Bu), 1.3 (s, t-Bu-H).

A-7

C: 52.61 (52.80), H: 5.68 (5.70), N: 5.77 (5.86);
 δ 9.4 (s, CH=N), 8.4-7.1 (m, Aryl-H), 5.4 (s, CH_2), 1.56 (s, t-Bu), 1.32 (s, t-Bu-H).

A-9

C: 61.32 (61.09), H: 5.78 (5.75), N: 7.44 (7.38);
 δ 7.7-7.1 (m, Aryl-H), 4.7 (d, CH_2), 1.3 (d, t-Bu-H).

A-11

C: 62.33 (62.95), H: 5.60 (5.72), N: 2.41 (2.04), Cl: 15.83 (15.48).

A-13

C: 59.77 (59.80), H: 5.20 (5.32), N: 2.43 (2.11);
 δ 8.4 (s, CH=N), 8.0-7.1 (m, Aryl-H), 1.6 (d, t-Bu), 1.3 (d, t-Bu-H).

A-14

C: 60.98 (59.33), H: 5.39 (5.29), N: 4.55 (4.32), Cl: 16.76 (16.42);
 δ 7.5-7.1 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (s, t-Bu-H).

A-18

C: 54.99 (54.42), H: 3.77 (3.57), N: 5.32 (5.52);
 δ 8.0 (s, CH=N), 7.4-6.1 (m, Aryl-H).

A-19

δ 8.2 (s, CH=N), 8.8-6.9 (m, Aryl-H).

A-20

C: 48.79 (49.08), H: 3.72 (3.81), N: 2.39 (2.12);
 δ 8.9 (s, CH=N), 7.5-6.8 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, t-Bu-H).

A-21

Ti: 8.39 (8.16);
 δ 7.6-6.8 (m, Aryl-H), 3.9 (s, CH_2), 2.4 (s, CH_3), 1.4 (s, t-Bu), 1.3 (s, t-Bu).

A-28

Ti: 8.99 (9.16);

δ 8.4 (s, CH=N), 7.5-6.8 (m, Aryl-H), 1.4, 1.3 (t-Bu, Me).

A-29

Ti: 7.31 (7.11);

δ 8.7 (s, CH=N), 7.6-6.8 (m, Aryl-H), 2.8 (s, CH₂).

A-30

Ti: 8.20 (8.43);

δ 8.4 (s, CH=N), 8.0-6.9 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, Me).

A-31

Ti: 7.01 (6.87);

δ 8.4 (s, CH=N), 7.9-7.1 (m, Aryl-H), 1.4 (s, t-Bu-H), 1.3 (s, t-Bu).

A-32

Ti: 8.07 (8.19);

9.2 (s, CH=N), 7.9-6.9 (m, Aryl-H).

A-33

Ti: 7.78 (7.75);

8.8 (s, CH=N), 7.7-7.2 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.35 (s, t-Bu-H).


A-34

Ti: 8.91 (9.82);

δ 8.3 (s, CH=N), 7.7-6.9 (m, Aryl-H), 1.5 (s, t-Bu-H), 1.3 (s, t-Bu).

Example 26

B-6 (35%); **B-9** (52%); **B-13** (38%); **B-19** (23%) were prepared as the said general procedure.

[0078]

The following are part of analysis results: (Anal.: Found (Calc.); ¹H NMR, 300 MHz CDCl₃)

B-6

δ 9.1 (s, CH=N), 9.6 (d, pyridine-1H), 8.6 (d, pyridine-1H), 7.9-7.3 (m, Aryl-H).

B-9

C: 58.01 (57.26), H: 5.78 (5.39), N: 1.77 (2.02);

δ 7.8-6.6 (m, Aryl-H), 1.2 (s, t-Bu-H).

B-13


δ 8.4 (s, CH=N), 8.1-7.0 (m, Aryl-H), 1.5 (d, t-Bu-H), 1.3 (d, t-Bu-H).

B-19

δ 8.1 (s, CH=N), 8.6-6.5 (m, Aryl-H).

Example 27 Synthesis of complex **C-1**


[0079] To a solution of ligand **L1** 300 mg (0.6 mmol) in THF of 10 ml at 0°C, was added NaH (0.6 mmol) in THF of 10 ml, stirred for additional 1h at room temperature, after the solvent was removed under vacuum, 25 ml of acetonitrile was added to the residue, the anionic solution was added to a solution of FeCl₃ (97 mg, 0.6 mmol) in CH₃CN at 0°C, the mixture was stirred at room temperature overnight. The mixture was heated to 80°C and stirred for an additional 1h, cooled slowly and filtered, the solvent was concentrated to give **C-1**, 296mg (79.6%).



Anal.: Found (Calc.) C: 70.80 (71.48), H: 7.46 (7.45), N: 5.49 (5.75).

Example 28 Synthesis of complex D-1


[0080] To a solution of ligand **L1** 300 mg (0.6 mmol) in 10 ml of THF at 0°C, was added dropwise a solution of NaH (0.6 mmol) in 10 ml of THF, stirred for 1h at room temperature, the anionic solution was added to a solution of FeCl₂ (76 mg, 0.6 mmol) in 10 ml of THF, stirred for 40h at room temperature, the solvent was removed under vacuum, the mixture was dissolved in 20 ml of CH₂Cl₂, filtered to give clear green solution, concentrated to give **D-1**, 135mg (38.5%).



Anal.: Found (Calc.) C: 66.80 (67.08), H: 6.46 (6.04), N: 2.49 (2.40), Cl: 6.55 (6.07).

Example 29 Synthesis of complex D-8


[0081] A solution of ligand **L8** 159 mg (0.37 mmol) in 15 ml of THF was added to a suspension of KH 15 mg (0.37 mmol) in 5 ml of THF at -78°C, warmed slowly to room temperature, stirred for 1h, anhydrous FeCl₂ was added to the anionic solution, stirred overnight and anhydrous ethyl ether was added, centrifugalizing, the organic layer was removed solvent, the crude product was recrystallized from CH₂Cl₂/hexane to give complex **D-8**, 208 mg (68%).



Anal. Found: (Calc.): C: 57.48 (58.11), H: 3.39 (3.51), N: 5.41 (5.42), Fe: 10.46 (10.81).

Example 30

[0082] **D-16** (83%), **D-18** (57%), **D-21** (69%), **D-22** (80%) were prepared by the said general procedure.



The following are part of analysis results:

D-16

Fe: 8.44 (8.38);

FID-MS (M^+): 666.

D-18

Fe: 12.41 (12.56);

FID-MS (M^+): 444.

D-21

Fe: 9.98 (10.66);

FID-MS (M^+): 523.

D-22

Fe: 9.41 (9.97);

FID-MS (M^+): 560.


Example 31 Synthesis of complex E-9

[0083] A solution of ligand L2 476 mg (1.0 mmol) in 50 ml of THF was added drop wise to a suspension of KH 43 mg (1.1 mmol) in 15 ml of THF at -78°C , stirred for 3h at room temperature. The anionic solution was added drop wise to a solution of $\text{ZrCl}_4 \cdot 2\text{THF}$ (1.0 mmol) in 15ml of THF, after refluxing and stirring overnight, the solvent was removed under vacuum, the residue was dissolved completely in 20 ml of CH_2Cl_2 , centrifugalizing, the organic layer was concentrated, a few drops of hexane was added to the mixture, cooled to give crude product, the crude product was recrystallized to give complex B-2, 215 mg (32%).

[0084] Analogues were synthesized by the said general procedure.

Example 32 Synthesis of complex F-1

[0085] A solution of ligand L1 800 mg (1.62 mmol) in 20 ml of THF was added to a suspension of NaH (1.62mmol) in 10 ml of THF at 0°C to give yellow anionic solution, stirred for 1h at room temperature, a solution of TiCl_4 0.09 ml (0.8 mmol) in 5 ml of THF was added to the said solution, stirred for an additional 3h at room temperature. The solvent was removed under vacuum, the mixture was dissolved in 20 ml of CH_2Cl_2 , centrifugalizing and the organic layer was concentrated under vacuum, cooled to give yellow crude product. recrystallized from toluene to give grange yellow product 550 mg (62.3%).




Anal.: Found (Calc.) C: 70.91 (71.81), H: 6.64 (6.39), N: 2.21 (2.54);

^1H NMR (300 MHz CDCl_3): δ 8.1 (s, HC=N), 7.6-7.0 (m, Aryl-H), 1.2 (s, t-Bu-H), 1.1 (s, t-Bu-H).

[0086] Analogues were synthesized by the said general procedure..

Example 33 Synthesis of complex G-1

[0087] A solution of ligand L1 300 mg (0.6 mmol) in 10 ml of THF was added to a suspension of NaH (0.6 mmol) in 10 ml of THF at 0°C, stirred for 1h at room temperature, the solution was added to $\text{ZrCl}_4 \cdot 2\text{TNF}$ (0.3 mmol) in 3ml of THF, after remaining the temperature of 0°C for 0.5h, refluxing for 5.5h, the solvent was removed under vacuum, the mixture was dissolved in 20 ml of CH_2Cl_2 , centrifugalizing, cooled to give yellow crude product, recrystallized from CH_2Cl_2 /hexane to give G-1, 94 mg (27.3%).




Anal. Found: (Calc.) C: 68.98 (69.09), H: 6.17 (6.15), N: 2.49 (2.44);
FID-MS (M^+): 1148.

[0088] Analogues were synthesized by the said general procedure

Example 34 Synthesis of complex H-1

[0089] A solution of ligand L1 591 mg (1.2 mmol) in THF of 10 ml was added to a suspension of NaH (1.2 mmol) in THF of 10 ml at 0°C, stirred for an additional 1h at room temperature, a solution of $(\text{Ph}_3\text{P})_2\text{NiPhCl}$ (780mg, 1.1mmol) in 10 ml of THF was added to the anionic solution, stirred overnight at room temperature, and then refluxed for 1 h, cooled to room temperature and filtered, the solvent was removed under vacuum, the residue was dissolved in 20 ml of hexane and filtered, the filtrate was concentrated to give H-1, 325 mg (47%).



Anal.: Found (Calc.) C: 73.80 (74.54), H: 7.46 (7.45), N: 5.49 (5.75).

[0090] Analogues were synthesized by the said general procedure.

Example 35

[0091] To a solution of complex A-9 200 mg in 10 ml THF at -78°C, was added MeMgBr (4 equiv.) in ethyl ether of 5 ml, warmed to room temperature, stirred overnight, the solvent was removed under vacuum, filtered and the filtrate was concentrated to give trialkylate compound of A-9, 325 mg (47%).

Anal.: ^1H NMR (300 MHz C_6D_6): δ 9.1 (s, CH=N), 7.8-6.8 (m, Aryl-H), 1.3 (s, t-Bu-H), 1.1 (s, t-Bu-H), 0.7 (s, CH_3).

[0092] Analogues were synthesized by the said general procedure.

Example 36

[0093] A round-bottom flask of 100 ml was charged with a solution of catalyst A-1 (2 μ mol), toluene 20ml under 0.1MPa of ethylene, stirred quickly, keep it at 50 °C for a period of time, mMAO(Al/Ti =1500) was added, stirred quickly for 0.5h. quenching the reaction by 5 HCl/ethanol. The precipitated polymer was filtered and washed, dried at 50°C under vacuum to constant weight, giving polyethylene 1.80g. The activity is 1.8×10^6 g PE/molTi hr atm. and M_w = 630,000g/mol, polymer weight distribution is 2.13, T_m =136.1°C.

Example 37

[0094] A round-bottom flask of 100 ml was charged with a solution of catalyst A-1 (2 μ mol), toluene 20ml under 0.1MPa of ethylene, stirred quickly, keep it 50°C for a period of time, mMAO(Al/Ti=1500) was added, stirred quickly for 0.5 h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered and washed, dried at 50°C under vacuum to constant weight, giving polyethylene 1.22g. The activity is 1.2×10^6 g PE/molTi hr atm. and $M_w = 700,000$ g/mol, polymer weight distribution is 2.06, $T_m = 134.5^\circ\text{C}$, crystalline grade 78%.

Example 38

[0095] A round-bottom flask of 100 ml was charged with a solution of catalyst A-1 (2 μ mol), toluene 20ml under 0.1MPa of ethylene, stirred quickly, keep it 50°C for a period of time, mMAO(Al/Ti=1500) was added, stirred quickly for 0.5 h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered and washed, dried at 50°C under vacuum to constant weight, giving polyethylene 0.9422g. The activity is 0.94×10^6 g PE/molTi hr atm. and $M_w = 720,000$ g/mol, $T_m = 134.5^\circ\text{C}$, crystalline grade 80%.

Example 39

[0096] A 2L autoclave was charged with a solution of toluene 600ml and MAO (4.3ml 15%) under ethylene atmosphere, stirred for 15 min at room temperature, added A-1 (23 μ mol) in 10 ml of hexane, raising the pressure of the ethylene to 6×10^5 Pa under stirring quickly, the ethylene gas was removed after 1 h, the precipitated polymer was filtered and washed, dried at 50°C under vacuum to constant weight, giving polyethylene 31.5g. $M_w = 700,000$ g/mol.

Example 40

[0097] A flask of 100 ml was charged with a solution of toluene 20ml and Et_3Al (Al/Cat = 1000(mol)) under 0.1MPa of ethylene atmosphere, stirred quickly, keep it in 40°C for a period of time, catalyst A-1 (2 μ mol) was added, 10 h later, quenching the reaction by 10% HCl/ethanol. The precipitated polymer was filtered and washed, dried at 50°C under vacuum to constant weight, giving polyethylene 0.14g.

Example 41

[0098] A flask of 100 ml was charged with a solution of methylbenzene 20ml and mMAO (Al/Ti=1000) under 0.1MPa of ethylene, stirred quickly, then put it in an 50°C oil bath, keep the temperature for a period of time, catalyst F-1 (1.9 μ mol) was added, after reacting for 1 h, quenching the reaction by 5% HCl/ethanol. The polymer was precipitated, filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.104g. Catalytic activity is 5.5×10^4 g PE/molTi hr atm. The polymer molecular weight $M_w = 32,000$ g/mol, the molecular distribution is 2.03.

Example 42

[0099] A flask of 100 ml was charged with a solution of toluene 20ml and mMAO (Al/Ti=1000) under 0.1 MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst B-1 (2.06 μ mol) was added, after reacting for 0.5 h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.52g. Activity is 5.0×10^5 g PE/molTi hr atm. $M_w = 530,000$ g/mol, the molecular distribution is 2.11.

Example 43

[0100] A flask of 100 ml was charged with toluene 20ml and mMAO (Al/Ti=300) under 0.1MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst B-7 (1.6 μ mol) was added, after reacting for 0.5 h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.47g. Activity is 5.9×10^5 g PE/molTi hr atm. $M_w = 670,000$ g/mol, the molecular distribution is 2.47.

Example 44

[0101] A flask of 100 ml was charged with toluene 20ml and mMAO (Al/Ti=300) under 0.1MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst A-7 (5.2 μ mol) was added, after reacting for 0.5 h, quenching

the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.77g. Activity is 3.0×10^5 g PE/mol Ti hr atm. $M_w = 640,000$ g/mol, the molecular distribution is 2.45.

5 Example 45

[0102] A flask of 100 ml was charged with toluene 20ml and MMAO (Al/Cat=500 (mol)) under 0.1 MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-9 (2 μ mol) was added, after reacting for 3 min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.55g.

Example 46

15 [0103] A flask of 100 ml was charged with toluene 15ml and MMAO (Al/Cat =500 (mol)) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst E-9 (3 μ mol) in toluene was added, after reacting for 3 min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.412g.

Example 47

20 [0104] A flask of 100 ml was charged with toluene 15ml and MMAO (Al/Cat =500 (mol)) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst B-9 (6 μ mol) in toluene was added, after reacting for 1h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was, filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.064g.

Example 48

25 [0105] A flask of 100 ml was charged with toluene 15ml and MMAO (Al/Cat =500 (mol)) under 0.1 MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-9 (8 μ mol) in toluene was added, after reacting for 3h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.37g.

Example 49

35 [0106] A flask of 100 ml was charged with toluene 15ml and MMAO (Al/Cat =500) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-4 (8 μ mol) in toluene was added, after reacting for 0.5h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.91g.

40 Example 50

[0107] A flask of 100 ml was charged with toluene 15ml and MMAO (Al/Cat =500 (mol)) under 0.1MPa of ethylene at room temperature, stirred quickly, then keep it at 50°C for a period of time, catalyst A-2 (9 μ mol) was added, after reacting for 3h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.45g.

Example 51

50 [0108] A flask of 100 ml was charged with toluene 10ml and MMAO (Al/Cat =500) under 0.1MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst A-13 (30 μ mol) was added, after reacting for 20min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.70g.

Example 52

55 [0109] A flask of 100 ml was charged with toluene 10ml and MMAO (Al/Cat =500) under 0.1MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst A-2 (3 μ mol) was added, after reacting for 1h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to

constant weight, giving polyethylene 0.34g.

Example 53

- 5 [0110] A flask of 100 ml was charged with toluene 10ml and MMAO (Al/Cat =500) under 0.1MPa of ethylene, stirred quickly, then keep it at 50°C for a period of time, catalyst B-2 (5 μ mol) was added, after reacting for 1h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polyethylene 0.4g.

10 Example 54

- [0111] A flask of 100 ml was charged with toluene 10ml and MMAO (Al/Cat=500) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-4 (10.5 μ mol) in toluene was added, after reacting for 73min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C
15 under vacuum to constant weight, giving polyethylene 1.37g. The content of hexene is 11%.

Example 55

- 20 [0112] A flask of 100 ml was charged with toluene 20ml and MMAO (Al/Ti=1000) under 0.1MPa of ethylene, stirred quickly, keep it at 0°C for a period of time, catalyst C-1 (13 μ mol) was added, after reacting for 1h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, dried at 50°C under vacuum to constant weight, giving polyethylene 0.0051g. Activity is 3.9×10^2 g PE/molTi hr atm. $M_w = 21,000$ g/mol. polymer weight distribution is 2.21.

25 Example 56

- [0113] A flask of 100 ml was charged with toluene 20ml and MMAO (Al/Cat =1000) under 0.1MPa of ethylene, stirred quickly, catalyst C-8 (16 μ mol) was added at room temperature, after reacting for 1h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, dried at 50 °C under vacuum to constant weight. giving
30 ethylene oligomer 0.7g.

Example 57

- 35 [0114] A flask of 100 ml was charged with toluene 20ml and MMAO (Al/Cat=1000) under 0.1 MPa of ethylene at room temperature, stirred quickly, catalyst C-18 (22 μ mol) was added, after reacting for 3h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 0.003g.

Example 58

- 40 [0115] A flask of 100 ml was charged with toluene 20ml and MMAO (Al/Cat=1000) under 0.1MPa of ethylene at room temperature, stirred quickly, catalyst C-16 (15 μ mol) was added, after reacting for 3h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 0.005g.

45 Example 59

- [0116] A ampulla of 15 ml was charged with a solution of catalyst A-1 (16 μ mol, 7.2×10^{-3} M in toluene) and AlEt₃ (Al/Ti=20), stirred quickly, keep it at 50°C for a period of time, 1ml of hexene was added, after reacting for 1h, quenching
50 the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, dried at 50°C under vacuum to constant weight, giving polyethylene 0.12g. Activity is 0.75×10^4 g PE/mol Ti hr atm. $M_w = 18,000$ g/mol.

Example 60

- 55 [0117] A Ampulla of 15 ml was charged with a solution of catalyst A-1 (18 μ mol, 7.2×10^{-3} M in toluene) and AlEt₃ (Al/Ti=20), stirred quickly, keep it in 50°C for a period of time, 1ml of methyl methacrylate was added, after reacting for 12h, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, dried at 50°C under vacuum to constant weight, giving polymethylmethacrylate 0.1721g. Activity is 0.96×10^4 g PE/molTi hr atm. $M_w =$

220,000g/mol. molecular weight distribution is 2.1.

Example 61

- 5 [0118] A 2L autoclave was charged with toluene 400ml and MAO (6ml, 15%) under nitrogen, stirred for 15 min at room temperature, added 10 ml of catalyst A-1 (29 μ mol) in toluene, stirring quickly, propene was added. The pressure of the system was remained 18×10^5 Pa, after reacting for 0.5 h, the propene gas was vented, the polymer was precipitated, filtered, washed, dried at 50°C under vacuum to constant weight, giving polypropene 5.3g.

10 Example 62

- 15 [0119] A flask of 100 ml was charged with a solution of 1-hexene 0.5 ml, toluene 5ml and MMAO (Al/Cat=500) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-1 (9 μ mol) was added, then toluene 9.5ml was added (the whole volume was 15ml), after reacting for 10min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 1.49g. The content of hexene is 5%.

Example 63

- 20 [0120] A flask of 100 ml was charged with 1-hexene 10 ml and MMAO (Al/Cat =500) under 0.1 MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-1 (9 μ mol) was added, then toluene was added to the whole volume is 15ml, after reacting for 10min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 2.9g. The content of hexene is 30%.

25

Example 64

- 30 [0121] A flask of 100 ml was charged with a solution of norbornene 2 ml in toluene (norbornene wt%=67%), toluene 15 ml and MMAO (Al/Cat=500) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-1 (9 μ mol) was added, after reacting for 20min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 0.89g. The content of norbornene is 15%.

Example 65

35

- [0122] A flask of 100 ml was charged with a solution of norbornene in toluene 25 ml (norbornene wt%=67%), toluene 15 ml and MMAO (Al/Cat=500) under 0.1MPa of ethylene, stirred quickly, then keep it at 40°C for a period of time, catalyst A-1 (9 μ mol) was added, after reacting for 20min, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, then dried at 50°C under vacuum to constant weight, giving polymer 0.42g. The content of norbornene is 40%.

40

Example 66

- 45 [0123] A flask of 25 ml was charged with a solution of hexene 2ml, 15ml toluene and MMAO (Al/Cat=200) under 0.1MPa of nitrogen, stirred quickly, then keep it at 50°C for a period of time, catalyst A-1 (18 μ mol) was added, after reacting for 1 h, quenching the reaction by 5% HCl/ethanol. Treated as general method give polymer 0.32g.

Example 67

- 50 [0124] A flask of 25ml was charged with a solution of norbornene in toluene 2ml (norbornene w%=67%), toluene and MMAO (Al/Cat=500) under 0.1MPa of nitrogen, stirred quickly, then keep it at 50°C for a period of time, catalyst A-1 (15 μ mol) was added, after reacting for 1 h, quenching the reaction. Treated as general method give polymer 0.052g.

55 Example 68

- [0125] A flask of 20ml was charged with a solution of methyl methacrylate 1ml, toluene and MMAO (Al/Cat=20 (mol)) under 0.1 MPa of nitrogen, stirred quickly, then keep it at 50°C for a period of time, catalyst A-1 (18 μ mol) was added,

after reacting for 12h, quenching the reaction. Treated as general method give polymer of 0.18g.

Example 69

5 [0126] A flask of 100ml was charged with a solution of norbornene in toluene 2ml (norbornene wt%=67%), toluene 5ml and MMAO (Al/Cat=500) under 0.1MPa of nitrogen, stirred quickly, then keep it at 40°C for a period of time, catalyst A-9 (12 μ mol) was added, after 10min, quenching the reaction. Treated as general method give polymer 0.72g, the content of norbornene is 21%.

10 Example 70

[0127] A Schlenk flask of 100ml was charged with a solution of 1-hexene 2ml, toluene 5ml, and MMAO (Al/cat=500) under 0.1MPa of ethylene, stirred quickly, keep it at 40°C for a period of time, catalyst A-9 (9 μ mol) was added, 20 min later, quenching the reaction by 10% HCl/ethanol. The precipitated polymer was filtrating, washing, dried at 50°C under vacuum to constant weight, yield 1.51g and the content of hexene is 22%.

Example 71

20 [0128] A Schlenk flask of 100 ml was charged with a solution of 1-hexene 2ml, toluene 5ml, and MMAO (Al/cat=500) under 0.1MPa of ethylene atmosphere, stirred quickly, keep it at 40°C for a period of time, catalyst E-9 (4.5 μ mol) was added, 15 min later, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtrated, washed, dried at 50°C under vacuum to constant weight, yield 0.85 g and the content of hexene is 4.5%.

Example 72

25 [0129] A Schlenk flask of 100 ml was charged with a solution of 1-hexene 2ml, toluene 5ml, and MMAO (Al/cat=500) under 0.1MPa of ethylene atmosphere, stirred quickly, keep it at 40°C for a period of time, catalyst E-9 (4.5 μ mol) was added, 15 min later, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtrating, washing, dried at 50°C under vacuum to constant weight, yield 0.85 g and the content of hexene is 4.5%.

Example 73

30 [0130] A flask of 100 ml was charged with a solution of trialkylated compound of catalyst A-1 (2 μ mol), toluene 20ml, under 0.1MPa of ethylene atmosphere, stirred quickly, keep it at 40°C for a period of time, mMAO (Al/Ti=500) was added, 0.5h later, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed and dried at 50°C under vacuum to constant weight, give polyethylene 0.24g.

Example 74

40 [0131] A flask was charged with treated SiO₂ (160m²g⁻¹, 60Å, 63-200 μ m) 500mg and solution of complex A-1 (200mg) in 30 ml of toluene in turn, heated to 100°C, stirred overnight. Filtered, the solid was washed with 20 ml of toluene for several times, dried under vacuum for 10h, thus obtained the supported catalyst.

[0132] A flask of 100 ml was charged with the supported catalyst (2 μ mol) and toluene 20ml under 0.1MPa of ethylene, stirred quickly, keep it at 50°C for a period of time, mMAO(Al/Ti=500) was added, 0.5h later, quenching the reaction by 5% HCl/ethanol. The precipitated polymer was filtered, washed, dried at 50°C under vacuum to constant weight, give polyethylene 2.6g.

Claims

50 1. A catalyst or catalytic system for olefin polymerization and copolymerization, the catalyst has the following formula:

→ : is single bond or double bond;

.....: is coordination bond, covalent bond or ionic bond;

- : is covalent bond or ionic bond;

m: 1, 2 or 3;

g: 0 or 1;

d: 0 or 1;



M: transition metal from group 3 to group 11, examples of M are Ti, Zr, Ni, Pd, Fe, Co;

n: 1, 2, 3 or 4;

X is hydrogen, halogen, hydrocarbyl substituted hydrocarbyl group containing oxygen atom, group containing nitrogen atom, group containing sulfur atom, group containing boron atom, group containing aluminum atom, group containing phosphor atom, group containing silicon, group containing germanium atom or group containing selenium atom, each X in the formula could be the same or not, two or more can be linked to form one or more cyclic substitutes;

The absolute value of total negative charges of all ligands in the formula is as same as the absolute value of positive charges of metal M in the formula, the ligands include each X and multidentate ligand;

A is O, S, Se,



B is a group containing nitrogen atom, a group containing phosphor atom or hydrocarbyl;

D is O, S, Se, a group containing nitrogen atom, a group containing phosphor atom, a group containing selenium atom, sulfonyl and sulfoxidyl ;

E refers to the group containing nitrogen atom, the group containing oxygen atom, the group containing sulfur atom, the group containing selenium atom, the group containing phosphor atom wherein the N, O, S, Se and P are coordination atoms;

G refers to an inert group, examples of the said inert group include hydrocarbyl, substituted hydrocarbyl and inert functional group;

B, E, G could link to one another;

- A "hydrocarbyl" is a univalent group containing only carbon and hydrogen, including alkyl group, cycloalkyl group, alkenyl group, alkynyl group, aromatic group, condensed rings group, heterocyclic group. If not otherwise stated, it is preferred that hydrocarbyl group herein containing 1 to about 30 carbon atoms;
- A "substituted hydrocarbyl" refers to a hydrocarbyl which contains one or more substituent groups which are inert under the process conditions to which the compound containing these groups is subjected. The substituent groups also do not substantially interfere with the process. In another word, these substituent groups do not coordinate with metal. If not otherwise stated, it is preferred that hydrocarbyl group herein contain 1 to about 30 carbon atoms. Included in the meaning of "substituted hydrocarbyl" are aromatic group, heteroaromatic rings, condensed rings group, heterocyclic group;
- A "inert functional group" herein refers to a group other than hydrocarbyl or substituted hydrocarbyl which is inert under the process conditions to with the compound containing the group is subjected. The functional groups also do not substantially interfere with any process described herein that the compound in which they are present may take part in. The functional group herein include a group containing oxygen atom, a group containing nitrogen atom, a group containing silica atom, a group containing germanium atom, a group containing sulfur atom or group containing stannum atom. Examples of functional groups include halogen (fluorine, chlorine, bromine and iodine), ether ($-OR^{34}$ or $-TOR^{34}$), ester of C_1-C_{10} , amine of C_1-C_{10} , alkoxy of C_1-C_{10} , nitril group. In case in which the functional group may be near an metal atom, the functional group should not coordinate to the metal atom more strongly than the group A, D, E, F, Y, Z which containing coordination atom and are shown as coordinating to metal atom, that is they should not displace the desired coordinating group:
 - A "halogen" herein is fluorine, chlorine, bromine and iodine;
 - A "group containing nitrogen atom" herein is



$-NR^{23}R^{24}$, $-T-NR^{23}R^{24}$, $-N(O)R^{25}R^{26}$, or $-T-N(O)R^{25}R^{26}$;

T is hydrocarbyl, substituted hydrocarbyl and inert functional group. If not otherwise stated, it is preferred that group herein contain 1 to about 30 carbon atoms;

- A "group containing phosphor atom" herein is




$PR^{28}R^{29}$, $-P(O)R^{30}R^{31}$, $-P(O)R^{32}(OR^{33})$, $-T-PR^{28}R^{29}$, $-T-P(O)R^{30}R^{31}$ or $-T-P(O)R^{32}(OR^{33})$;

- A "ether" herein is $-OR^{34}$ or $-TOR^{34}$;
- A "group containing oxygen atom" herein is hydroxyl, alkoxy ($-OR^{34}$), group with such as $-T-OR^{34}$;
- A "group containing sulfur atom" herein is $-SR^{35}$, $-T-SR^{35}$, $-S(O)R^{36}$, $-T-SO_2R^{37}$;
- A "group containing selenium atom" herein is $-SeR^{38}$, $-T-SeR^{38}$, $-T-Se(O)R^{39}$, $-Se(O)R^{39}$;
- A "group containing boron atom" herein is BF_4^- , $(C_6F_5)_4B^-$, $(R^{40}BAr_3)^-$ etc.;
- A "group containing aluminum atom" herein is alkyl aluminum compound, $AlPh_4^-$, AlF_4^- , $AlCl_4^-$, $AlBr_4^-$, AlI_4^- , $R^{41}AlAr_3^-$;
- A "group containing silicon atom" herein is $-SiR^{42}R^{43}R^{44}$, $-T-SiR^{45}$;
- A "group containing germanium atom" herein is $-GeR^{46}R^{47}R^{48}$, $-T-GeR^{49}$;
- A "group containing stannum atom" herein is $-SnR^{50}R^{51}R^{52}$, $-T-SnR^{53}$, $-T-Sn(O)R^{54}$;
- A "alkyl aluminum compound" herein is a compound in which at least one alkyl group is bound to aluminum atom, and halogen can also be bound to aluminum atoms in the compound. Examples of alkyl aluminum compound include methyl aluminoxane(MAO), modified methyl aluminoxane (MMAO), $AlEt_3$, $AlMe_3$, $Al(i-Bu)_3$;

- $R^1, R^2, R^3, R^{22}, R^{23}, R^{24}, R^{25}, R^{26}, R^{27}, R^{28}, R^{29}, R^{30}, R^{31}, R^{32}, R^{33}, R^{34}, R^{35}, R^{36}, R^{37}, R^{38}, R^{39}, R^{40}, R^{41}, R^{42}, R^{43}, R^{44}, R^{45}, R^{46}, R^{47}, R^{48}, R^{49}, R^{50}, R^{51}, R^{52}, R^{53}, R^{54}$ are each independently hydrogen, halogen (F, Cl, Br, I), hydrocarbyl, substituted hydrocarbyl or inert functional group. Each group above may be the same or not, and that any two of them which are vicinal may be linked to one another or to form a ring;
- A "catalytic system" herein is the system formed by catalyst mentioned above, or catalyst combined with cocatalyst W, or the catalyst supported on the carrier, or catalyst together with cocatalyst W supported on the carrier, or polymeric catalyst or polymeric catalyst combined with cocatalyst W;
- A "carrier" herein is polymer materials, silica, alumina, magnesium chloride titanium dioxide or the mixtures of two or more materials mentioned above.
- A "cocatalyst" herein is (a) a kind of neutral Lewis acid which could abstract X^- from the metal to form $(WX)^-$, and which is also capable of transferring an alkyl group or a hydride group to M, provided that $(WX)^-$ is a weakly coordinating anion. Examples of this kind of neutral Lewis acid include MAO and MMAO; or (b) a combination of following two kind of compounds, one kind compound is capable of transferring an alkyl or hydride group to metal and the other kind of compound is capable of abstracting X^- from the metal and form weakly coordinating anion. Examples of the former kind of compound include alkyl aluminum compound such as $AlEt_3$, $AlMe_3$, $Al(i-Bu)_3$ and the examples of the latter kind of compound include cationic Lewis acid ($Na[B(3,5-(CF_3)_2C_6H_3)_4]$ or $Ag[B(3,5-(CF_3)_2C_6H_3)_4]$, $NaOSO_2CF_3$ or $AgOSO_2CF_3$), alkyl aluminum compound or borane ($B(C_6F_5)_3$ etc.);

A "weakly coordinating anion" herein is the anion whose coordinating ability is known and has been discussed in the literature, see for instance W. Beck, et al., Chem. Rev., vol. 88, p. 1405-1421 (1988), and S. H. Strauss, Chem. Rev., vol. 93, p. 927-942 (1993), both of which are hereby included by reference. Among such anions are those formed from the aluminum compounds in the immediately preceding paragraph and X^- , including $(R^{41})_3AlX^-$, $(R^{41})_2AlX_2^-$, $(R^{41})AlX_3^-$, " $R^{41}AlOX^-$ ". Other useful weakly coordinating anions include *p*-toluenesulfonate, SbF_6^- , PF_6^- , BF_4^- , $(C_6F_5)_4B^-$, $(R^1SO_2)_2N^-$, $CF_3SO_3^-$ or $((3,5-(CF_3)_2C_6H_3)_4B^-$.

2. A catalyst or catalytic system for olefin polymerization and copolymerization as recited in claim 1, the catalyst has the following formula:



wherein:

.....: refers to coordination bond, covalent bond or ionic bond;


—: refers to covalent bond or ionic bond;

The descriptions of "A", "B", "E", "G", "d", "q", "m", "M", "n", "X", "R¹", "R²" and "R³" are each independently as same as those recited in claim 1;

F is group containing oxygen atom, group containing nitrogen atom, group containing sulfur atom or group containing selenium atom, and among which the coordination atom is N, O, S, Se, P;

The descriptions of "catalytic system", "group containing oxygen atom", "group containing nitrogen atom", "group containing sulfur atom", "group containing phosphor atom" and "group containing selenium atom" are each independently as same as those recited in claim 1.

3. A catalyst or catalytic system for olefin polymerization and copolymerization as recited in claim 2, the catalyst has the following formula:



15 wherein:

.....: refers to coordination bond, covalent bond or ionic bond;


—: refers to covalent bond or ionic bond;

20 R⁴, R¹⁰, R¹¹, R¹² are each independently hydrogen, halogen, hydrocarbyl, substituted hydrocarbyl, or inert functional group, each said group may be same or different, and any two of the groups vicinal to one another may link to each other or form a ring;

The descriptions of "A", "E", "F", "G", "d", "q", "m", "M", "n", "X", "R¹", "R²" and "R³" are each independently as same as those recited in claim 2;

25 The descriptions of "catalytic system", "hydrocarbyl", "substituted hydrocarbyl" and "inert functional group" are each independently as same as those recited in claim 1.

4. A catalyst or catalytic system for olefin polymerization and copolymerization as recited in claim 3, the catalyst has the following formula:



50 wherein:

.....: refers to coordination bond, covalent bond or ionic bond;

—: refers to covalent bond or ionic bond;

55 R⁶, R⁷, R⁸, R⁹: are each independently hydrogen, halogen, hydrocarbyl, substituted hydrocarbyl, or an inert functional group;


The descriptions of "A", "E", "F", "G", "d", "q", "m", "M", "n", "X", "R³", "R⁴", "R¹⁰", "R¹¹" and "R¹²" are each independently as same as those recited in claim 3;

R³, R⁴, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹¹, R¹² may be same or different, and any two of the groups vicinal to one another may link to each other or form a ring;

The descriptions of "catalytic system", "hydrocarbyl" and "substituted hydrocarbyl" are each independently as

same as those recited in claim 1.

5. A catalyst or catalytic system for olefin polymerization and copolymerization as recited in claim 4, the catalyst has the following formula:



wherein:

.....: refers to coordination bond, covalent bond or ionic bond;

—: refers to covalent bond or ionic bond;

Which, E binds M by coordination bond, A binds M by covalent bond and D binds M by coordination bond or by covalent bond;

R¹⁰, R¹¹, R¹², R¹³, R¹⁴, R¹⁵, R¹⁶, R¹⁷, R¹⁸, R¹⁹, R²⁰, R²¹ are each independently hydrogen, halogen, hydrocarbyl, substituted hydrocarbyl, or an inert functional group. Each said group may be same or different, and any two of the groups vicinal to one another may link to each other or form a ring;


R⁵ is the lone pair electron of nitrogen atom, H, hydrocarbyl, substituted hydrocarbyl, group containing oxygen atom, group containing sulfur atom, group containing nitrogen atom, group containing phosphor atom. When R⁵ is one of the groups containing oxygen atom or sulfur atom or nitrogen atom or selenium atom or phosphor atom, the N or O or S or P or Se atom in the group may coordinate with metal (M);

Y and Z are each independently group containing oxygen atom, group containing nitrogen atom, group containing sulfur atom, group containing phosphor atom or group containing selenium atom;

The descriptions of "T", "M", "X", "n", "catalytic system", "hydrocarbyl", "substituted hydrocarbyl", "group containing oxygen atom", "group containing nitrogen atom", "group containing sulfur atom", "group containing phosphor atom" and "group containing selenium atom" are each independently as same as those recited in claim 1.

6. The synthesis procedure of catalyst used for the olefin polymerization and copolymerization as recited in claim 1 wherein the catalyst is prepared in organic solvent by mixing the ligand or the anion of the ligand with transition metal complex in mole ration 1:0.1~6 for 0.5~4.0 hours under the -78°C to reflux temperature;

The ligand has the following formula:



wherein the descriptions of "d", "A", "B", "D", "E", "G", "→", "—", "R¹", "R²" and "R³" are each independently as same as those recited in claim 1;

7. The synthesis procedure of catalyst used for the olefin polymerization and copolymerization as recited in claim 1 wherein transition metal complex used in claim 6 has the formula MX_g, wherein g is 1, 2, 3, 4, 5 or 6; the descriptions of M and X are each independently as same as those recited in claim 1."

8. The usage of catalyst or catalytic system used for the olefin polymerization and copolymerization as recited in

claim 1 wherein the catalyst or catalytic system with/without cocatalyst could catalyze olefin oligomerization, polymerization and copolymerization as homogeneous catalyst or heterogeneous catalyst; The said homogeneous catalyst is meant the catalyst or the catalytic system used directly without supported on the carrier; The said heterogeneous catalyst is meant the catalyst or the catalytic system used after supported on the carrier such as polymer materials, silica, alumina, magnesium chloride etc. or the mixtures of the said carrier; The said olefin is meant ethylene, α -olefin, styrene, alkenoic acid and its derivatives, alkenols and its derivatives, diene, cycloalkene, norbornene and its derivatives and other alkene with functional group; The said α -olefin is meant an alkene containing 1 to 30 carbon such as propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, 4-methyl-1-pentene and mixtures of them; The said cycloalkene is meant cyclopentene, cyclohexene, norbornene and its derivatives; The said alkene with functional group is meant an alkene containing one or more inert functional group, such as vinyl acetate, phenylacetylene, acrylonitrile, acrylamide, alkenyl ether and alkenyl ester.

9. The usage of catalyst or catalytic system used for the olefin polymerization and copolymerization as recited in claim 8 wherein the said copolymerization is meant the copolymerization of ethylene with α -olefin, the copolymerization of the ethylene with alkene with functional group, the copolymerization of α -olefin with alkene containing functional group and the copolymerization between the α -olefins; The descriptions of the said "olefin", "alkene with functional group" and " α -olefin" are independently as same as those recited in claim 8.
10. The usage of catalyst or catalytic system used for the olefin polymerization and copolymerization as recited in claim 8 wherein the catalyst could be used directly, or used after supported on the carrier, or used as polymeric catalyst, or used as catalytic system.
11. The usage of catalyst or catalytic system used for the olefin polymerization and copolymerization as recited in claim 8 wherein the said carrier is meant polymer materials, silica, alumina, magnesium chloride etc. or the mixtures of the said supports.
12. The usage of catalyst or catalytic system used for the olefin polymerization and copolymerization as recited in claim 8 wherein the said the catalyst or catalytic system could be used as homogeneous or heterogenous catalyst (or catalytic system) to (co)polymerization olefin under the following conditions: polymerization pressure is 0.1~10Mpa, polymerization temperature is -50~150°C, the mole ratio of catalyst vs cocatalyst is 1:1~5000. The descriptions of "catalyst", "catalytic system" and "cocatalyst" are each independently as same as those recited in claim 1. The description of "olefin" is as same as those recited in claim 8.




Fig. 1

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN02/00425

A. CLASSIFICATION OF SUBJECT MATTER

Int. Cl⁷ C08F4/60,10/02

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched(classification system followed by classification symbols)

Int. Cl⁷ C08F4/60,4/62,4/64,10/00,110/00,210/00,C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the field searched

Electronic data base consulted during the international search(name of data base and, where practicable, search terms used)

WPI,EPODOC,PAJ,EPPAT,USPAT,CNPAT

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant claim No.
P	US,B,6281303 (EASTMAN CHEMICAL COMPANY) 28.AUG. 2001 (28.08.01), column10-13, example 1, claim31-34.	1-12
X	CN,A,1297456 (EXXON CHEM PATENTS INC) 30.May 2001 (30.05.01), page5-8.	1-12
X	WO,A,0132723 (W.R.GRACE & CO.-CONN.) 10.MAY 2001(10.05.01) claim3.	1-12

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason(as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"G" document member of the same patent family

Date of the actual completion of the international search

17.September 2002(17.09.02)

Date of mailing of the international search report

03 OCT 2002

Name and mailing address of the ISA/

The Chinese Patent Office
:6, Xitucheng Road, Haidian District,
Beijing, 100088, China

Facsimile No. 86-10-62019451

Authorized officer

Cao Xianpeng

Cao Xianpeng

Telephone No. (86-010) 62093057

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.

PCT/CN02/00425

Patent document cited in search report	Publication date	Patent family members	Publication Date
US-B-6281303	28-08-01	NONE	NONE
CN-A-1297456	30-05-01	WO-A-9957159	11-11-99-
		BR-A-9908887	21-11-00
		EP-A-1084152	21-03-01
		US-B-6294495	25-09-01
WO-A-0132723	10-05-01	AU-A-1096001	14-05-01

Form PCT/ISA/210(patent family annex)(July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

IMAGES ARE

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.